


























TECHNICAL CHARACTERISTICS

wineo 600					wineo	
Covering type according to EN ISO 10582: Heterogeneous resilient-flooring for glueless installation						
	wineo 600 wood	wineo 600 wood „Patchwork“	wineo 600 wood XL	wineo 600 stone	wineo 600 stone XL	
Format	1212 x 187 mm	1212 x 185 mm	1505 x 237 mm	600 x 317 mm	914 x 480 mm	
Product thickness	5 mm	5 mm	5 mm	5 mm	5 mm	
Planks, tiles / m² per box	8 / 1.81 m ²	8 / 1.79 m ²	6 / 2.14 m ²	10 / 1.90 m ²	6 / 2.63 m ²	
Boxes / m² per pallet	64 / 115.84 m ²	64 / 114.56 m ²	56 / 119.84 m ²	60 / 114.00 m ²	44 / 115.72 m ²	
Guarantee	20 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de					
Classification					Product composition	
	Utilization class 23 Heavy-duty use in the domestic area EN ISO 10874		Corridors, living rooms, kitchens, home offices		1	Surface sealing
	Utilization class 32 Normal use in the commercial sector EN ISO 10874		Offices, boutiques, cafés		2	Surface texture various embossings
	Utilization class 41 Medium use in the light industrial sector EN ISO 10874		Workshop for precision mechanics		3	Wear layer Thickness 0.4 mm
	Wear layer binder content EN ISO 10582		Type I		4	Decor Decor film
	Wear resistance EN 660-2		Group T acc. to DIN EN 649:2011-05		5	Base layer with glass fibre reinforced
	Reaction to fire EN 13501-1		B _{fl} - s1		6	Profile connection Connect technology 
	Anti slip category DIN 51130		R 9		7	Backing
	Slip resistance EN 13893		$\mu \geq 0.30$ - DS			Insulation mat silentCOMFORT (separately available)
	Anti-static properties EN 1815		≤ 2 kV		Certifications	
	Staining and chemical resistance EN ISO 26987		Good resistance according to the concentration and residence time		 <p>windmüller flooring products WFP GmbH Nord-West-Ring 21 D-32832 Augustdorf</p> <p>- 09 -</p> <p>Elastischer Bodenbelag DOP: 0501002 EN 14041:2004</p>   <p>Resilient Flooring to be used within a building.</p>  <p>EMISSIONS DANS L'AIR INTERIEUR</p> <p>Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classes allant de C (fortes émissions) à A+ (très faibles émissions)</p>  <p>Schadstoffgeprüft Emissionsgeprüft</p>  <p>PROFI</p>  <p>factory made coated</p>	
	Light fastness EN ISO 105-B02		≥ 6			
	Residual indentation EN ISO 24343-1		~ 0.07 mm			
	Castor chair test EN 425 / ISO 4918		Type W – no visible change			
	Thermal resistance EN 12667		~ 0.033 (m ² K)/W ~ 0.0254 (m ² K)/W in combination with silentCOMFORT			
	Impact sound reduction EN ISO 16251-1		~ 7 dB up to 14 dB in combination with silentCOMFORT			
	Dimension stability EN ISO 23999		~ 0.1 %			
	Disposal		Private: Possible with normal domestic refuse Commercial: Refuse-key-no. AVV 170203			

Relevant information:

- Installation in utilization class 41 possible (vehicular traffic excluded).
- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by windmüller flooring products WFP GmbH.